

## CALCIUM SULFONATE EP #2 GREASE

#### **Excellent Rust Protection**

High Dropping Point for High Temperature Applications



REV:

07.06.2017



# **DESCRIPTION**

SynGard™ Calcium Sulfonate EP 2 Grease is high performance extreme pressure grease exhibiting outstanding film strength and resistance to corrosive saltwater environments. With a Timken OK load of 65 lbs., SynGard Calcium Sulfonate EP 2 Grease is recommended for the most severe applications in industry. It is particularly suitable for high speed bearings and centralized lubrication systems. Exhibiting excellent water repellency, oxidation resistance and a wide operating temperature range.

### **BENEFITS**

- Excellent performance under heavy loads
- Protects equipment from rust
- Does not drip out under running conditions
- Extraordinary performance at high temperatures
- Protects equipment from rusting under humid and water ingress conditions

### **APPLICATION**

SynGard Calcium Sulfonate EP 2 Grease is recommended for use in automotive, as well as extreme pressure applications in the construction, mining, agricultural, logging and hauling industries and anyplace where a shear stable, high load carrying, corrosion resistant grease is required.

TYPICA	L PROPERTIES	METHOD	SynGard Calcium Sulfonate EP #2 Grea
TI	nickener		Calcium Sulfonate
NL	GI Grade		2
-	lexture lexture	Visual	Smooth
Colo	r, Observed		Amber
Worke	d Penetration	D-217	265-295
Droppir	g Point, °C (°F)	D-2265	288 (550) Min.
Wheel Bea	ring Leakage, gm	D-1263	5.0 Max
Water Wash	out @ 79.4°C, % wt	D-1264	3.0
Base Oil Vis	cosity @ 40°C, cSt	D-445	220
Wel	d Load, kg	D-2596	620
Load	Wear Index	D-2596	65

D-2509



#### NOTE:

The information on this Product Data Sheet is believed to be accurate and is typical of current production.

Specifications are subject to change without notice.

Timken OK Load, Ib

**Health And Safety Information** See separate Safety Data Sheets available on request.

 $\textbf{SynGard}^{\text{TM}} \ \textbf{and} \ \textbf{Martin Lubricants}^{\text{TM}} \ \textbf{are} \ trademarks \ of \ \textbf{Martin Lubricants}. \ \textbf{All other marks are property of their respective owners}$ 



65